


---

**Norm:** ASTM A475 - Standard Specification for Zinc-Coated Steel Wire Strand

---

**Applications & Usage:**

Galvanized steel strand used in electrical and distribution networks.

---

**Dimensional Characteristics**

Nominal Conductor Diameter	: 1/2" (12.70 mm)
Number of Strands	: 19
Nominal Diameter of Steel Strands:	: 0.100" (2.54 mm)
Approximate Weight	: 504 lb./1000 ft (751 kg/km)
Stranding Lay (unless otherwise specified)	: Left Lay

**Mechanical Characteristics**

**Common Grade**

Minimum Breaking Strength of Strand	: 7,620 lbf (33.895 kN)
Minimum Elongation (24" or 610 mm)	: 10%

**Siemens-Martin Grade (SM)**


Minimum Breaking Strength of Strand	: 12,700 lbf (56.492 kN)
Minimum Elongation (24" or 610 mm)	: 8%

**High Strength Grade (HS)**

Minimum Breaking Strength of Strand	: 19,100 lbf (84.961 kN)
Minimum Elongation (24" or 610 mm)	: 5%

**Extra High Strength Grade (EHS)**

Minimum Breaking Strength of Strand	: 26,700 lbf (118.768 kN)
Minimum Elongation (24" or 610 mm)	: 4%



---

### Galvanization Characteristics

Nominal Diameter of Steel Strands : 0.100" (2.54 mm)

Minimum Weight of Coating Zinc of Uncoated Wire Surface

- Class 1 - 0.30 oz/ft<sup>2</sup> (92 g/m<sup>2</sup>)
- Class A - 0.70 oz/ft<sup>2</sup> (214 g/m<sup>2</sup>)
- Class B - 1.40 oz/ft<sup>2</sup> (427 g/m<sup>2</sup>)
- Class C - 2.10 oz/ft<sup>2</sup> (641 g/m<sup>2</sup>)

### Packaging

Material & Type of Packaging : Heat-Treated Wooden Reels (HT 284 / ISPM-15)

Length of Cable per Reel : As requested by client