


---

**Norm:** ASTM A475 - Standard Specification for Zinc-Coated Steel Wire Strand

---

**Applications & Usage:**

Galvanized steel strand used in electrical and distribution networks.

---

**Dimensional Characteristics**

Nominal Conductor Diameter	: 7/16" (11.11 mm)
Number of Strands	: 7
Nominal Diameter of Steel Strands:	: 0.145" (3.68 mm)
Approximate Weight	: 399 lb./1000 ft (595 kg/km)
Stranding Lay (unless otherwise specified)	: Left Lay

**Mechanical Characteristics**

**Utilities Grade (UTIL)**

Minimum Breaking Strength of Strand	: 18,000 lbf (80.068 kN)
Minimum Elongation (24" or 610 mm)	: 4%

**Common Grade**

Minimum Breaking Strength of Strand	: 5,700 lbf (25.355 kN)
Minimum Elongation (24" or 610 mm)	: 10%

**Siemens-Martin Grade (SM)**


Minimum Breaking Strength of Strand	: 9,350 lbf (41.591 kN)
Minimum Elongation (24" or 610 mm)	: 8%

**High Strength Grade (HS)**

Minimum Breaking Strength of Strand	: 14,500 lbf (64.499 kN)
Minimum Elongation (24" or 610 mm)	: 5%

**Extra High Strength Grade (EHS)**

Minimum Breaking Strength of Strand	: 20,800 lbf (92.523 kN)
Minimum Elongation (24" or 610 mm)	: 4%



---

### **Galvanization Characteristics**

Nominal Diameter of Steel Strands : 0.145" (3.68 mm)

Minimum Weight of Coating Zinc of Uncoated Wire Surface

- Class 1 - 0.40 oz/ft<sup>2</sup> (122 g/m<sup>2</sup>)
- Class A - 0.90 oz/ft<sup>2</sup> (275 g/m<sup>2</sup>)
- Class B - 1.80 oz/ft<sup>2</sup> (549 g/m<sup>2</sup>)
- Class C - 2.70 oz/ft<sup>2</sup> (824 g/m<sup>2</sup>)

### **Packaging**

Material & Type of Packaging : Heat-Treated Wooden Reels (HT 284 / ISPM-15)

Length of Cable per Reel : As requested by client